

COPYRIGHT 2006 DERWENT INFORMATION LTD

TITLE: Method for fabricating magnesium diboride
superconducting wire

INVENTOR: SHIN, J G

PATENT-ASSIGNEE: LG ELECTRONICS INC[GLDS]

PRIORITY-DATA: 2001KR-0045655 (July 28, 2001)

PATENT-FAMILY:

PUB-NO	PUB-DATE	LANGUAGE	PAGES	MAIN-IPC
KR 2003010964 A	February 6, 2003	N/A	001	H01B 012/00

APPLICATION-DATA:

PUB-NO	APPL-DESCRIPTOR	APPL-NO	APPL-DATE
KR2003010964A	N/A	2001KR-0045655	July 28, 2001

INT-CL (IPC): H01B012/00

ABSTRACTED-PUB-NO: KR2003010964A

BASIC-ABSTRACT:

NOVELTY - A method for fabricating a magnesium diboride superconducting wire is provided to improve mechanical intensity by forming magnesium diboride on a surface of a wire.

DETAILED DESCRIPTION - A boron fiber(1) is formed by covering boron on a tungsten core layer. In order to fabricate magnesium diboride by using a diffusion method, the boron fiber(1) is flown in the inside of a chamber(2). Magnesium vapor(6) is injected into the inside of the chamber(2). Magnesium chips of a boat(3) are flown by using a thermal evaporation method or an e-beam evaporation method or an ion beam deposition method or a sputtering method. A deoxidation gas such as a hydrogen gas is injected into the inside of the chamber(2) in order to prevent oxidation of boron. A wire collection portion(5) and a wire supply portion(7) are installed in the inside of the chamber(2). The boat(3) is formed with a tungsten material or an alumina material.

CHOSEN-DRAWING: Dwg.1/10

TITLE-TERMS: METHOD FABRICATE MAGNESIUM SUPERCONDUCTING WIRE

DERWENT-CLASS: U14 X12